TASMANIA

TASIBEL
NATURAL FIBRE FLOORING




Made In Belgium


TASMANIA



8561



8562




8563



8565

TASMANIA

TASIBEL
NATURAL FIBRE FLOORING



Col. 8565

SPECIFICATION

Manufacturing Process	Flat Woven, Loop Pile	
Pile Composition	20% Wool, 80% Sisal	
Secondary Backing	Felt	
Total Height	8,7mm	
Pile Weight	2050 g/m²	
Total Weight	3625 g/m²	
Width	ca. 400 cm	
Length	ca. 30m	
Resistance of Heat Conduction	ISO 8302	0,074 m² K/W
Tog Rating	0,74	
Sound Insulation	18 db	
Suitability	Medium Domestic	
	Moderate commercial	
Fire Resistance	Cfl-s1	

EN 14041
DOP: 1104-122512
NB: 0493
15
CE
Cfl-s1 G NCS DL PCP NA HCHO
λ_{23}
FOR USE AS FLOOR COVERING IN BUILDINGS.
Tasibel NV
Industrielaan 16
Belgium - 8520 Kuurne

TESTED FOR A BETTER LIVING ENVIRONMENT
GUT
2EBA0A9E
www.gut-prodis.eu

Made In Belgium