




MIPOLAM CLASSIC

gerflor.com



Gerflor[®]
theflooringgroup



0014 Brown



0301 Beige



0003 Ivory



0005 Steel



0002 Platinum



0010 Azure



			MIPOLAM CLASSIC 1.5 mm	MIPOLAM CLASSIC 2 mm
DESCRIPTION				
Total Thickness	EN ISO 24346 (EN 428)	mm	2.0	2.0
Weight	EN ISO 23997 (EN 430)	g/sq.m	2520	3300
Width/Length of Sheet	EN ISO 24341 (EN 426)	cm/lm	200/20	200/20
Tile size	EN ISO 24342 (EN 427)	mm	-	300 x 300* / 608 x 608
Number of tiles per package	-	-	-	50 / 20
CLASSIFICATION				
Norm/Product Specification	-	-	EN ISO 10581 (EN 649)	EN ISO 10581 (EN 649)
European classification	EN ISO 10874 (EN 685)	class	23-31	34-43
Fire Rating	EN 13 501-1	class	Bfl-s1	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2	< 2
PERFORMANCE				
Wear resistance	EN 660.2	mm³	≤ 15	≤ 7.5
Wear Group	NF 189	group	F	M
Type Binder content	EN ISO 10581	type	II	II
Dimensional stability	EN ISO 23999 (EN 434)	%	≤ 0.40	sheet ≤ 0.40 tile ≤ 0.25
Residual indentation	EN ISO 24343-1 (EN 433)	mm	≈ 0.03	≈ 0.03
Castor Chair test (type W)	ISO 4918 (EN 425)	-	OK	OK
Thermal Conductivity	EN ISO 10456 (EN 12524)	W/(m.K)	0.25	0.25
Colour Fastness	EN 20 105-B02	degree	≥ 6	≥ 6
Surface Treatment	-	-	PUR	PUR
Chemical Products fastness	EN ISO 26987 (EN 423)	class	OK	OK
ENVIRONMENT / INDOOR AIR QUALITY				
TVOC after 28 days	ISO 16000-6	µg/ m³	< 10	< 10
CE MARKING				
CE	EN 14 041	-		
				

Product description & technical data sheet in *Dutch / French, Spanish / Portuguese, Italian, Swedish, Norwegian* on Gerflor websites.

INSTALLATION
Laying is the responsibility of the installer. Installation should be made in accordance with installation guidelines supplied and regularly updated by Gerflor’s Technical Department. Installation should be carried out in accordance with local standards. Subfloor to be smooth, hard, clean and dry prior to laying. Where applicable the subfloor must incorporate an effective Damp Proof Membrane. The material must be allowed to acclimatise 24 hours prior to installation in a room temperature of between 18-24°C. All seams must be heat welded using Gerflor matching weld rod.

MAINTENANCE
Maintenance should be carried out regularly to retain the appearance and durability of the floor. The floor covering should be maintained with regular sweeping and damp mopping using a neutral cleaner, or auto scrubber machine with an appropriate pad.
 Rubber leaves indelible stains on vinyl floorings: do not use mats with rubber backing and replace tubular furniture feet with those made of PVC or polyamide. Place mats of sufficient length at entrances to reduce outside sources of dirt.
Further installation and maintenance instructions are available from Gerflor.

MIPOLAM CLASSIC, LESS SPEAKING FOR MORE ACTIONS



COMPOSITION
100% REACH compliant



INDOOR AIR QUALITY
100 times below standards
(TVOC < 10 ug/m³ after 28 days)



RECYCLED CONTENT
25 %



RECYCLABILITY
100 %



LCA
Eco-designed according to a product specific life cycle analysis



WELLNESS
Walking comfort: B class