



RECREATION



Gerflor[®]

theflooringgroup


All Gerflor experience for a highly performing recreational floor: environmental friendly, low VOC, no solvent, no heavy metal and 100% recyclable suitable for leisure and sports activities.

RECREATION 45

 1,50 m	 PUR Protect®	 100 % recyclable
---	---	--



6563 Menta




RECREATION 60

 1,50 m	 PUR Protect®	 100 % recyclable
---	---	--



2402 Azul





6563 Menta



6160 Naranja




6556 Verde



6154 Roja




2402 Azul



2711 Gris



6614 Oceano*



6157 Rosa*



6062 Canadian Maple



6058 American Oak

* Only available in Recreation 60

RECREATION					
PRODUCT DESCRIPTION DESCRIPCIÓN DEL PRODUCTO ОПИСАНИЕ	Standard / Norma / Стандарт	Requirement / Requisito / Требование	Units / Unidades / Единицы	RECREATION 45	RECREATION 60
Surface treatment / Tratamiento de superficie / Обработка поверхности	-	-	-	PUR PROTECT	PUR PROTECT
Surface complex / Complejo de superficie / Состав поверхности	-	-	-	100% PVC	
Foam / Espuma / Вспененная подложка	-	-	-	Closed cell foam / Espuma de celdas cerradas / Упорядоченная структура ячеек	
Thickness / Espesor / Толщина	EN 428	-	mm	4.5	6.0
Weight / Peso / Вес	EN 430	-	kg/m²	2.6	3.7
Length / Largo / Длина	EN 426	-	lm	20.5	20.5
Width / Ancho / Ширина	EN 426	-	lm	1.5	1.5

SPORT PROPERTIES
CARACTERÍSTICAS DEPORTIVAS / СПОРТИВНЫЕ ХАРАКТЕРИСТИКИ

Shock absorption / Amortiguación / Амортизация ударов	EN 14808	≥ 25	%	≤ 25	≥ 25
Vertical deformation Deformación vertical / Вертикальная деформация	EN 14809	≤ 3.5	mm	≤ 3.5	≤ 3.5
Sliding coefficient / Coeficiente de deslizamiento / Коэффициент скольжения	EN 13036-4	80 - 110	-	80 - 110	80 - 110
Ball bounce / Rebote de balón / Отскок мяча	EN 12235	≥ 90	%	≥ 90	≥ 90

TECHNICAL CHARACTERISTICS
CARACTERÍSTICAS TÉCNICAS / ЭКСПЛУАТАЦИОННЫЕ ХАРАКТЕРИСТИКИ

Abrasion resistance / Resistencia a la abrasión / Износостойкость	EN ISO 5470-1	≤ 1000	mg	≤ 350	≤ 350
Impact resistance / Resistencia al impacto / Ударопрочность	EN 1517	≥ 8	N/m	≥ 8	≥ 8
Indentation resistance / Resistencia al punzonamiento / Остаточные впадины	EN 1516	≤ 0.5	mm	≤ 0.5	≤ 0.5

CLASSIFICATION / CLASIFICACIÓN / КЛАССИФИКАЦИЯ

Fire / Fuego / Огнестойкость	EN 13501-1	-	-	Cfl-s1	Cfl-s1
------------------------------	------------	---	---	--------	--------

RECREATION, LESS SPEAKING, MORE ACTIONS



COMPOSITION
100% REACH



RECYCLED CONTENT
30%



RECYCLABILITY
100%



INDOOR AIR QUALITY
10 times lower than norms requirements
(TVOC < 100µg/m³ after 28 days)



WELLNESS
Foam Backing
for Safety