
## **Tapiflex Excellence 65 Uni**

**ACOUSTIC HETEROGENEOUS VINYL** 









# Sustainable product lines

#### Great acoustic properties with Tapiflex Excellence

With its foam backing the acoustic efficiency of Tapiflex Excellence is 19 dB. Its unique structure made of recycled vinyl offers high indentation resistance (0.12 mm). Its pure vinyl top layer is reinforced with our TOPCLEAN XPTM polyurethane treatment that increases its resistance to abrasion and scratches. The Sanitized® treatment is also applied. The TOPCLEAN XPTM treatment also eliminates wax or polish for life, which significantly reduces maintenance costs.

## Tapiflex Excellence and Acczent Excellence are solid evidence of Tarkett's environmental actions.

- Tapiflex and Acczent Excellence are designed with strong environmental concern, from production to disposal.
- They offer eco-friendly properties, thanks to their easy and low cost maintenance and the reduced need for water, energy, and detergents.









#### Make your balanced choice

Tarkett's approach to sustainability is all about giving our customers simple and clear information so they can make the right choice of flooring, balancing their project and budget requirements beside the need for sustainable solutions.

Choose to use bettermaterials – natural and renewable where possible



Select flooring produced with fewer resources





products that contribute to wellbeing in peoplefriendly spaces



Reuse and recycle materials through participating in recycling









### Specification

Printed acoustic vinyl floorcovering with high density foam backing on a glass fibre stabilized carrier, filler free wear layer.
PUR reinforcement, built in fungistatic and bacteriostatic Sanitized® treatment.

Product standard: EN 651.

CERTIFICATION & CLASSIFICATION	STANDARDS	Tapiflex Excellence 65 Uni
Type of floorcovering	EN 651	Heterogeneous Acoustic Vinyl
	EN 649	
CE certification	EN 14041	Yes
UPEC classification		U4P3E2/3C2*
Impact sound reduction	EN ISO 140-8 EN ISO 717-2	ΔL <sub>W</sub> 19 dB
Acoustical improvement	NF S31-074	$L_{n,e,w} = 61 \text{ dB}$
NF UPEC. A+ certificate	NF 189	*Registration in progress ref n°10.4020/1 & 2 since 25/02/2011 (valid one year)
Classification	EN 685	34
TECHNICAL CHARACTERISTICS	STANDARDS	Tapiflex Excellence 65 Uni
Wear layer thickness	EN 429	0.65 mm
Surface treatment		TopClean XP
Total thickness	EN 428	3.45 mm
Abrasion group	EN 660-1	Group T : ≤ 0,08 mm
Total weight	EN 430	3 240 g/m²
Form of delivery	EN 426 Sheet (rolls)	approx. 23 running metres x 200 cm
	EN 427 Tiles (box)	
TECHNICAL PERFORMANCES	STANDARDS	Tapiflex Excellence 65 Uni
Dimensional stability	EN 434	< 0.10%
Reaction to fire	EN 13501-1	Bfl s1 on fibrecement substrate A2fl Cfl s1 on woodchip substrate
Static indentation	EN 433	0.12 mm
Castor chair	EN 425	No damage
Underfoot comfort	EN 433	≥ 0.40 mm
Furniture leg	EN 424	No damage
Curl resultant to heat	EN 434	≤ 8 mm
Electrostatic properties	EN 1815	< 2 kV
	EN 1081	$R1 > 10^{10} \Omega$
From all about a sould be about a short a self-self-self-self-self-self-self-self-	EN 14041	Antistatic on concrete
Fungi static and bacteria static effect	NF EN ISO 846	Sanitized®
Chemical resistance	EN 423	High resistance
Thermal resistance Underfloor heating	EN 12524	0,05 m² K/W Suitable
Light fastness	EN ISO 105-B02	≥ 6/8
Slip resistance	DIN 51130 EN 13893	R9 ≥ 0,3
Colours		100

The above information is subject to modification for the benefit of further improvement (05/11).

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett for these instructions.































