



Taralay Impression Comfort

A unique, stunning and eco-friendly collection, designed just for you

Gerflor®

Taralay Impression Comfort

Gerflor
theflooringgroup



0528 - Walnut Cream

Design	: Wood
Product format	: Rolls
Sizes	: 25 ml x 2 m
Thickness :	
Compact	: 2 mm
Comfort	: 3.35
NCS	: 2005-Y40R
LRV	: 53,6

Made in France

- Extreme Stain Resistance, Easy Maintenance
- High Traffic Resistance, Long-lasting Appearance
- The Best Acoustic / Indentation Performance on the Market
- Ultra-realistic Designs
- Matt Effect







Taralay Impression Comfort

Gerflor
theflooringgroup



1070 - Habana 3D Vinales

Design	: Wood
Product format	: Rolls
Sizes	: 25 ml x 2 m
Thickness : Compact	: 2 mm
NCS	: 3010-Y40R
LRV	: 35.50

Made in France

- Extreme Stain Resistance, Easy Maintenance
- High Traffic Resistance, Long-lasting Appearance
- The Best Acoustic / Indentation Performance on the Market
- Ultra-realistic Designs
- Matt Effect







Gerflor theflooringgroup	TARALAY IMPRESSION COMFORT		
DESCRIPTION			
Total thickness	EN ISO 24346	mm	3.35
	ASTM F386-02	inch	0.13
Wearlayer thickness	EN ISO 24340	mm	0.65
	ASTM F410-02	inch	0.026
Weight	EN ISO 23997	g/sq.m	2825
Width of sheet	EN ISO 24341	cm	200
	-	feet - inch	6‘6“
Length of sheet	EN ISO 24341	lm	25
	-	feet - inch	82‘
CLASSIFICATION			
Norm / Product specification	-	-	EN 651
European classification	EN ISO 10874	class	34 - 42
Fire rating	EN 13 501-1	class	B_{fl}-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	EN 16165:2021 – Appendix B (DIN 51 130)	class	R10
PERFORMANCE			
Wear resistance	EN 660.2	mm^3	≤ 2.00
Wear group	-	group	T
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.20
Residual indentation (average value measured)	-	mm	≈ 0.08
Impact sound insulation	EN ISO 717-2	dB	19
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	Protecsol® 2
Chemical products resistance	EN ISO 26987	-	OK
Anti-bacterial activity (E. coli - S. aureus - MRSA) (1)	ISO 22196	-	> 99 % Inhibits growth
Antiviral activity (human coronavirus 229E) (1)	ISO 21702	-	99.7% after 2h
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m^3	< 10
Certification	-	-	Floorscore®
CE MARKING			
CE	EN 14041	-	
		-	

(1) The implementation of an effective cleaning regime is the best defence against infection